

PATENT ABSTRACTS OF JAPAN

(11)Publication number : 2002-020847

(43)Date of publication of application : 23.01.2002

(51)Int.Cl.

C22C 38/00

B22F 3/11

C22C 38/16

F16C 7/02

(21)Application number : 2000-138224

(71)Applicant : MITSUBISHI MATERIALS CORP
MITSUBISHI MOTORS CORP

(22)Date of filing : 11.05.2000

(72)Inventor : SHIMIZU TERUO
FUJIWARA SHINICHI
YAMAGUCHI TOSHIHIRO

(54) CONNECTING ROD MADE OF Fe-BASED SINTERED ALLOY HAVING HIGH STRENGTH AND HIGH TOUGHNESS

(57)Abstract:

PROBLEM TO BE SOLVED: To provide a connecting rod made of an Fe-based sintered alloy having high strength and high toughness, capable of thinning and reducing dimensions and capable of satisfactorily coping with the lightening and increasing of performances in various driving apparatus.

SOLUTION: This connecting rod is composed of an Fe-based sintered alloy having a composition containing, by mass, 2 to 6% Ni, 0.5 to 2.5% Cu, 0.5 to 1.3% Mo, 0.2 to 0.8% C, 0.1 to 0.3% P and 0.2 to 0.65% Mn, and the balance Fe with inevitable impurities and has a porosity of 2 to 8%.

LEGAL STATUS

[Date of request for examination]

04.09.2003

[Date of sending the examiner's decision of rejection]

[Kind of final disposal of application other than the examiner's decision of rejection or application converted registration]

[Date of final disposal for application]

[Patent number]

[Date of registration]

[Number of appeal against examiner's decision of rejection]

[Date of requesting appeal against examiner's decision of rejection]

[Date of extinction of right]

Copyright (C); 1998,2003 Japan Patent Office